

1. ČELIČNA UŽAD I LANCI Wire ropes and chains


1.3. Nerotirajuće uže

Čelično uže: 8 DURA PLUS CP čelična jezgra

Wire rope: 8 PLUS 8CP

CE 2.1 2.2 3.1 BL

Promjer (mm)	Min. prekidna sila (kN) 1960 N/mm ²	Min. prekidna sila (kN) 2160 N/mm ²	Težina (kg/100m)
Diameter	MBL	MBL	Weight
8	55,4	58,0	29,0
9	70,2	73,6	37,0
9,5	78,2	82,0	41,0
10	86,8	92,4	46,0
11	105,0	112,0	56,0
12	125,0	131,0	66,0
12,7	140,0	149,0	74,0
13	148,0	156,0	78,0
14	171,0	181,0	90,0
14,3	178,0	189,0	94,0
15	196,0	208,0	104,0
16	224,0	236,0	118,0
17	253,0	266,0	133,0
18	282,0	300,0	149,0
19	314,0	334,0	166,0
20	348,0	375,0	184,0
21	384,0	413,0	203,0
22	424,0	451,0	223,0
23	463,0	493,0	243,0
24	504,0	538,0	265,0
25	547,0	580,0	288,0
25,4	565,0	599,0	297,0
26	595,0	629,0	311,0
27	642,0	678,0	335,0
28	683,0	725,0	361,0
28,6	712,0	755,0	376,0
29	732,0	776,0	387,0
30	785,0	844,0	414,0
31	838,0	901,0	442,0
32	900,0	960,0	471,0
33	957,0	1021,0	501,0
34	1020,0	1084,0	532,0
35	1074,0	1140,0	560,0
36	1262,0	1205,0	596,0
38	1395,0	1349,0	664,0
40	1487,0	1480,0	736,0
41,3	1543,0	1578,0	784,0
42,0	1693,0	1640,0	811,0
44	1845,0	1800,0	891,0
46	2010,0	1967,0	973,0
48	2120,0	2140,0	1006,0
50	2180,0	2290,0	1150,0



- EN 12385-4
- nerotirajuće, vrlo savitljivo uže, vrlo otporno na trošenje
- završna obrada: crno, el. galvanizirano ili vruće cinčano
- čvrstoća žice: 1960 N/mm² ili 2160 N/mm²

